

AD-A104 105

SRI INTERNATIONAL MENLO PARK CA
DYNAMIC DEFORMATION AND FRACTURE OF PLAIN AND FILLED ELASTOMERS--ETC(U)
SEP 81 Y M GUPTA, W J MURRI

F/G 11/10

N00014-78-C-0549

NL

UNCLASSIFIED

1 1/2 1

20 20 20



END
DATE
FILMED
10-81
DTIC

AD A104105

SRI International

DTIC FILE COPY



LEVEL 1

12

DYNAMIC DEFORMATION AND FRACTURE OF PLAIN
AND FILLED ELASTOMERS

Final Report

September 1981

By: Y. M. Gupta and W. J. Murri

Prepared for:

OFFICE OF NAVAL RESEARCH
Power Program
Arlington, VA 22217

Attention: Dr. R. S. Miller (Code 473)

ONR Contract N00014-78-C-0549

SRI Project PYU 7802

DTIC
ELECTE
SEP 14 1981
H

12 13

DISTRIBUTION STATEMENT A
Approved for public release;
Distribution Unlimited

333 Ravenswood Ave. • Menlo Park, California 94025
(415) 326-6200 • Cable: SRI INTL MPK • TWX: 910-373-1246

81 9 11 064

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) DYNAMIC DEFORMATION AND FRACTURE OF PLAIN AND FILLED ELASTOMERS		5. TYPE OF REPORT & PERIOD COVERED Final Report Sept. 1978 - Sept. 1981
7. AUTHOR(s) Y. M. Gupta and W. J. Murri		6. PERFORMING ORG. REPORT NUMBER SRI Project PYU-7802
9. PERFORMING ORGANIZATION NAME AND ADDRESS SRI International 333 Ravenswood Avenue Menlo Park, CA 94025		8. CONTRACT OR GRANT NUMBER(s) N00014-78-C-0549
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Power Program Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE September 1981
		13. NUMBER OF PAGES 10
		15. SECURITY CLASS (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release, distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Mechanical response, Elastomer, High strain rate, Compression, Shear, Tension, Stress waves		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) To quantify the high strain-rate mechanical response of plain Solithane, compression, shear, and tension experiments were performed under impact loading (microsecond time scales). Compression and tension measurements were carried out for filled Solithane containing 56.5 wt% of glass beads. The results show that the compression response (uniaxial strain) of plain Solithane is dominated by the mean stress-volume relation. The bulk modulus under impact loading is considerably higher than that determined from static		

DD FORM 1473

JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Abstract (concluded)

measurements in the glassy state. The filled Solithane compression response can be approximated by a simple mixture theory using the Hugoniot of plain Solithane and glass.

Shear wave measurements in the plain Solithane were used to determine the shear modulus and the shear stress-strain response at several shock compressions. The shear modulus varied between 3 and 9 kbar for compressive stresses ranging between 2 and 14 kbar. With increasing compression, the dynamic shear modulus increases sharply in contrast to quasi-static measurements under pressure. The dynamic shear stress-strain curves show a decreasing modulus with increasing strain and suggest an elastic-plastic response with yield strength increasing from 0.12 to 0.25 kbar with increasing pressure for the compressive stress range investigated. This direct determination of the shear response will be very valuable for development of constitutive models because this information cannot be obtained from compression data.

Tension experiments on plain and filled Solithane show elastic-brittle fracture response for both materials. However, the threshold between no damage and full spall is considerably sharper for the filled Solithane. The sharper threshold is caused by the rapid linking of closely spaced cracks nucleated at the filler-matrix interface. The tensile damage is very localized, and the location can be predicted by simple wave interactions. Two experimental methods were attempted to quantify the fracture response on the microsecond time scales and to measure the fracture damage in the recovered specimens. These measurements have given encouraging results, but more work is needed before they can be used successfully. Because of a lack of quantitative measurements in previous studies, these measurements should be pursued in future work.

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Avail and/or	
Dist Special	
A	

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

TECHNICAL SUMMARY

The objectives of the work presented in this report were to directly determine the response of elastomers to compression, shear, and tension under dynamic loading conditions. These objectives have generally been met and a good start has been made in making these measurements. The main results are summarized below.

The compression results in plain Solithane are dominated by the mean stress-volume response. The bulk modulus under impact conditions is considerably higher than that determined from static hydrostatic loading. The response of the filled Solithane is stiffer and to a good approximation can be predicted by a simple mixture theory using the Hugoniot of glass and plain Solithane. The longitudinal modulus measured in impact experiments is similar to ultrasonic values and is bounded by the very high frequency (10^{10} Hz) and quasi-static measurements.

Shear wave profiles have been measured in plain Solithane at several compressions. The wave profiles are dispersive. With increasing compression, the dispersion decreases, but attenuation increases. The shear modulus values range between 3 and 9 kbar for compressive stresses ranging between 2 and 14 kbar. Unlike the quasi-static shear modulus, the dynamic data suggest a rapid increase with compression at higher stresses. High strain-rate, shear stress-strain curves have been obtained at three compression levels. The overall features are similar to quasi-static torsion measurements in glassy polymers under pressure. The stress-strain response is typical of an elastic-plastic solid with yield strength varying between 0.12 and 0.25 kbar for a volume compression ranging from 6% to 20%. The compression and shear data can be used to develop a realistic constitutive model at high strain rates.

Tension recovery experiments on plain and filled Solithane show an elastic-brittle response for both materials. The damage is quite localized, and the location can be predicted from simple wave interactions. Although the recovery experiments provide a good description of the fracture damage, it is difficult to quantify these experiments. Two types of measurements to quantify tensile fracture were attempted in the present work: (1) pull-back signal measurements to characterize the tensile strength and fracture kinetics on the microsecond time scale and (2) surface area measurements on recovered specimens using the BET method. Both of these measurements have given encouraging results, but further development is needed before they can be used successfully.

Future work should focus on the following topics:

- (1) Measurement of shear response above 15-kbar compression stress.
- (2) Measurement of shear response for filled Solithane to determine if these measurements can be correlated with the data for plain Solithane.
- (3) Attempts to quantify the tensile fracture damage.
- (4) Preliminary development of a dynamic constitutive model.

PUBLICATIONS AND PRESENTATIONS

1. Y. M. Gupta and W. J. Murri, "Response of a Plain and Filled Elastomer (Solithane 113) to High Strain-Rate Compression, Shear, and Tension Loading," Technical Report submitted to ONR under Contract N00014-78-C-0549, SRI International, Menlo Park, CA (January 1981).
2. Y. M. Gupta, W. J. Murri, and D. Henley, "Large Amplitude Compression and Shear Wave Propagation in an Elastomer," paper presented at the Topical Conference on Shock Waves in Condensed Matter held at SRI International Menlo Park, CA (June 1981); Bull. Am. Phys. Soc. 26, 657 (1981).
3. Y. M. Gupta and W. J. Murri, "High Strain Rate Fracture of Unfilled and Filled Elastomers," Bull. Am. Phys. Soc. 26 (March 1981).
4. Y. M. Gupta, "High Strain-Rate Shear Response of an Elastomer" (manuscript in preparation).

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. L.V. Schmidt Assistant Secretary of the Navy (R,E, and S) Room 5E 731 Pentagon Washington, D.C. 20350	1	Dr. F. Roberto Code AFRPL MKPA Edwards AFB, CA 93523	1
Dr. A.L. Slafkosky Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1	Dr. L.H. Caveny Air Force Office of Scientific Research Directorate of Aerospace Sciences Bolling Air Force Base Washington, D.C. 20332	1
Dr. Richard S. Miller Office of Naval Research Code 413 Arlington, VA 22217	10	Mr. Donald L. Ball Air Force Office of Scientific Research Directorate of Chemical Sciences Bolling Air Force Base Washington, D.C. 20332	1
Mr. David Siegel Office of Naval Research Code 260 Arlington, VA 22217	1	Dr. John S. Wilkes, Jr. FJSRL/NC USAF Academy, CO 80840	1
Dr. R.J. Marcus Office of Naval Research Western Office 1030 East Green Street Pasadena, CA 91106	1	Dr. R.L. Lou Aerojet Strategic Propulsion Co. P.O. Box 15699C Sacramento, CA 95813	1
Dr. Larry Peebles Office of Naval Research East Central Regional Office 666 Summer Street, Bldg. 114-D Boston, MA 02210	1	Dr. V.J. Keenan Anal-Syn Lab Inc. P.O. Box 547 Paoli, PA 19301	1
Dr. Phillip A. Miller Office of Naval Research San Francisco Area Office One Hallidie Plaza, Suite 601 San Francisco, CA 94102	1	Dr. Philip Howe Army Ballistic Research Labs ARRADCOM Code DRDAR-BLT Aberdeen Proving Ground, MD 21005	1
Mr. Otto K. Heiney AFATL - DLDL Elgin AFB, FL 32542	1	Mr. L.A. Watermeier Army Ballistic Research Labs ARRADCOM Code DRDAR-BLI Aberdeen Proving Ground, MD 21005	1
Mr. R. Geisler ATTN: MKP/MS24 AFRPL Edwards AFB, CA 93523	1	Dr. W.W. Wharton Attn: DRSMI-RKL Commander U.S. Army Missile Command Redstone Arsenal, AL 35893	1

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. R.G. Rhoades Commander Army Missile Command DRSMI-R Redstone Arsenal, AL 35898	1	Dr. E.H. Debutts Hercules Inc. Baccus Works P.O. Box 98 Magna, UT 84044	1
Dr. W.D. Stephens Atlantic Research Corp. Pine Ridge Plant 7511 Wellington Rd. Gainesville, VA 22065	1	Dr. James H. Thacher Hercules Inc. Magna Baccus Works P.O. Box 98 Magna, UT 84044	1
Dr. A.W. Barrows Ballistic Research Laboratory USA ARRADCOM DRDAR-BLP Aberdeen Proving Ground, MD 21005	1	Mr. Theodore M. Gilliland Johns Hopkins University APL Chemical Propulsion Info. Agency Johns Hopkins Road Laurel, MD 20810	1
Dr. C.M. Frey Chemical Systems Division P.O. Box 353 Sunnyvale, CA 94086	1	Dr. R. McGuire Lawrence Livermore Laboratory University of California Code L-324 Livermore, CA 94550	1
Professor F. Rodriguez Cornell University School of Chemical Engineering Olin Hall, Ithaca, N.Y. 14853	1	Dr. Jack Linsk Lockheed Missiles & Space Co. P.O. Box 504 Code Org. 83-10, Bldg. 154 Sunnyvale, CA 94088	1
Defense Technical Information Center DTIC-DDA-2 Cameron Station Alexandria, VA 22314	12	Dr. B.G. Craig Los Alamos National Lab P.O. Box 1663 NSP/DOD, MS-245 Los Alamos, NM 87545	1
Dr. Rocco C. Musso Hercules Aerospace Division Hercules Incorporated Allegheny Ballistic Lab P.O. Box 210 Washington, D.C. 21502	1	Dr. R.L. Rabie WX-2, MS-952 Los Alamos National Lab. P.O. Box 1663 Los Alamos NM 37545	1
Dr. Ronald L. Simmons Hercules Inc. Eglin AFATL/DLGL Eglin AFB, FL 32542	1	Dr. B. Rogers Los Alamos Scientific Lab. P.O. Box 1663 Los Alamos, NM 87545	1

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Mr. R. Brown Naval Air Systems Command Code 330 Washington, D.C. 20361	1	Dr. J. Schnur Naval Research Lab. Code 6510 Washington, D.C. 20375	1
Dr. H. Rosenwasser Naval Air Systems Command AIR-310C Washington, D.C. 20360	1	Mr. R. Beauregard Naval Sea Systems Command SEA 64E Washington, D.C. 20362	1
Mr. B. Sobers Naval Air Systems Command Code 03P25 Washington, D.C. 20360	1	Mr. G. Edwards Naval Sea Systems Command Code 62R3 Washington, D.C. 20362	1
Dr. L.R. Rothstein Assistant Director Naval Explosives Dev. Engineering Dept. Naval Weapons Station Yorktown, VA 23691	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, PA 19112	1
Dr. Lionel Dickinson Naval Explosive Ordnance Disposal Tech. Center Code D Indian Head, MD 20640	1	Dr. H.G. Adolph Naval Surface Weapons Center Code R11 White Oak Silver Spring, MD 20910	1
Mr. C.L. Adams Naval Ordnance Station Code PM4 Indian Head, MD 20640	1	Dr. T.D. Austin Naval Surface Weapons Center Code R16 Indian Head, MD 20640	1
Mr. S. Mitchell Naval Ordnance Station Code 5253 Indian Head, MD 20640	1	Dr. T. Hall Code R-11 Naval Surface Weapons Center White Oak Laboratory Silver Spring, MD 20910	1
Dr. William Tolles Dean of Research Naval Postgraduate School Monterey, CA 93940	1	Mr. G.L. Mackenzie Naval Surface Weapons Center Code R101 Indian Head, MD 20640	1
Naval Research Lab. Code 6100 Washington, D.C. 20375	1	Dr. K.F. Mueller Naval Surface Weapons Center Code R11 White Oak Silver Spring, MD 20910	1

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Mr. J. Murrin Naval Sea Systems Command Code 62R2 Washington, D.C. 20362	1	Dr. A. Nielsen Naval Weapons Center Code 385 China Lake, CA 93555	1
Dr. D.J. Pastine Naval Surface Weapons Center Code R04 White Oak Silver Spring, MD 20910	1	Dr. R. Reed, Jr. Naval Weapons Center Code 388 China Lake, CA 93555	1
Mr. L. Roslund Naval Surface Weapons Center Code R122 White Oak, Silver Spring MD 20910	1	Dr. L. Smith Naval Weapons Center Code 3205 China Lake, CA 93555	1
Mr. M. Stosz Naval Surface Weapons Center Code R121 White Oak Silver Spring, MD 20910	1	Dr. B. Douda Naval Weapons Support Center Code 5042 Crane, Indiana 47522	1
Dr. E. Zimmet Naval Surface Weapons Center Code R13 White Oak Silver Spring, MD 20910	1	Dr. A. Faulstich Chief of Naval Technology MAT Code 0716 Washington, D.C. 20360	1
Dr. D. R. Derr Naval Weapons Center Code 388 China Lake, CA 93555	1	LCDR J. Walker Chief of Naval Material Office of Naval Technology MAT, Code 0712 Washington, D.C. 20360	1
Mr. Lee N. Gilbert Naval Weapons Center Code 3205 China Lake, CA 93555	1	Mr. Joe McCartney Naval Ocean Systems Center San Diego, CA 92152	1
Dr. E. Martin Naval Weapons Center Code 3858 China Lake, CA 93555	1	Dr. S. Yamamoto Marine Sciences Division Naval Ocean Systems Center San Diego, CA 91232	1
Mr. R. McCarten Naval Weapons Center Code 3272 China Lake, CA 93555	1	Dr. G. Bosmajian Applied Chemistry Division Naval Ship Research & Development Center Annapolis, MD 21401	1
		Dr. H. Shuey Rohn and Haas Company Huntsville, Alabama 35801	1

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. J.F. Kincaid Strategic Systems Project Office Department of the Navy Room 331 Washington, D.C. 20376	1	Dr. C.W. Vriesen Thickol Elkhon Division P.O. Box 241 Elkhon, MD 21021	1
Strategic Systems Project Office Provision Unit Code SW2701 Department of the Navy Washington, D.C. 20376	1	Dr. J.C. Hinshaw Thickol Wasatch Division P.O. Box 524 Brigham City, Utah 84302	1
Mr. E.L. Throckmorton Strategic Systems Project Office Department of the Navy Room 1048 Washington, D.C. 20376	1	U.S. Army Research Office Chemical & Biological Sciences Division P.O. Box 12211 Research Triangle Park NC 27709	1
Dr. D.A. Flanigan Thickol Huntsville Division Huntsville, Alabama 35897	1	Dr. R.F. Walker USA ARADCOM DRDAR-LCC Dover, NJ 07801	1
Mr. G.F. Mangan Thickol Corporation Huntsville Division Huntsville, Alabama 35897	1	Dr. T. Sinden Munitions Directorate Propellants and Explosives Defence Equipment Staff British Embassy 3100 Massachusetts Ave. Washington, D.C. 20008	1
Mr. E.S. Sutter Thickol Corporation Elkhon Division P.O. Box 241 Elkhon, MD 21021	1	LTC B. Loving AFROL/LK Edwards AFB, CA 93523	1
Dr. G. Thompson Thickol Wasatch Division MS 240 P.O. Box 524 Brigham City, UT 84302	1	Professor Alan N. Gent Institute of Polymer Science University of Akron Akron, OH 44325	1
Dr. T.F. Davidson Thickol Corporation Thickol Corporation Government Offices Bldg. P.O. Box 1000 Casper, WY 82409	1	Mr. J. M. Frankle Army Ballistic Research Labs ARRADCOM Code DRDAR-BLI Aberdeen Proving Ground, MD 21005	1

DISTRIBUTION LIST

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Ingo W. May Army Ballistic Research Labs ARRADCOM Code DRDAR-BLI Aberdeen Proving Ground, MD 21005	1	Dr. J. P. Marshall Dept. 52-35, Bldg. 204/2 Lockheed Missile & Space Co. 3251 Hanover Street Palo Alto, CA 94304	1
Professor N.W. Tschoegl California Institute of Tech Dept. of Chemical Engineering Pasadena, CA 91125	1	Ms. Joan L. Janney Los Alamos National Lab Mail Stop 920 Los Alamos, NM 87545	1
Professor M.D. Nicol University of California Dept. of Chemistry 405 Hilgard Avenue Los Angeles, CA 90024	1	Dr. J. M. Walsh Los Alamos Scientific Lab Los Alamos, NM 87545	1
Professor A. G. Evans University of California Berkeley, CA 94720	1	Professor R. W. Armstrong Univ. of Maryland Department of Mechanical Eng. College Park, MD 20742	1
Professor T. Litovitz Catholic Univ. of America Physics Department 320 Michigan Ave., N.E. Washington, D.C. 20017	1	Prof. Richard A. Reinhardt Naval Postgraduate School Physics & Chemistry Dept. Monterey, CA 93940	1
Professor W. G. Knauss Graduate Aeronautical Lab California Institute of Tech. Pasadena, CA 91125	1	Dr. R. Bernecker Naval Surface Weapons Center Code R13 White Oak, Silver Spring, MD 20910	1
Professor Edward Price Georgia Institute of Tech. School of Aerospace Engin. Atlanta, Georgia 30332	1	Dr. M. J. Kamlet Naval Surface Weapons Center Code R11 White Oak, Silver Spring, MD 20910	1
Dr. Kenneth O. Hartman Hercules Aerospace Division Hercules Incorporated P.O. Box 210 Cumberland, MD 21502	1	Professor J. D. Achenbach Northwestern University Dept. of Civil Engineering Evanston, IL 60201	1
Dr. Thor L. Smith IBM Research Lab 042.232 San Jose, CA 95193	1	Dr. N. L. Basdekas Office of Naval Research Mechanics Program, Code 432 Arlington, VA 22217	1
		Professor Kenneth Kuo Pennsylvania State Univ. Dept. of Mechanical Engineering University Park, PA 16802	1

DISTRIBUTION LIST

	<u>No. Copies</u>	<u>No. Copies</u>
Dr. S. Sheffield Sandia Laboratories Division 2513 P.O. Box 5800 Albuquerque, NM 87185	1	
Dr. M. Farber Space Sciences, Inc. 135 Maple Avenue Monrovia, CA 91016	1	
Dr. Y. M. Gupta SRI International 333 Ravenswood Avenue Menlo Park, CA 94025	1	
Mr. M. Hill SRI International 333 Ravenswood Avenue Menlo Park, CA 94025	1	
Professor Richard A. Schapery Texas A&M Univ. Dept of Civil Engineering College Station, TX 77843	1	
Dr. Stephen Swanson Univ. of Utah Dept. of Mech. & Industrial Engineering MEB 3008 Salt Lake City, UT 84112	1	
Mr. J. D. Byrd Thiokol Corp. Huntsville Huntsville Div. Huntsville, AL 35807	1	
Professor G. D. Duvall Washington State University Dept. of Physics Pullman, WA 99163	1	
Prof. T. Dickinson Washington State University Dept. of Physics Pullman, WA 99163	1	

END

DATE
FILMED

10-81

DTIC